

Selecting Stainless Steel for Optimum Performance

Sponsor:
International Molybdenum
Association (IMOA)

Today's Goal

Learn why some stainless steel applications look fantastic after 80 years while others look bad after 6 months

Achieve Long Term Success

- Evaluate the environment
- Select the right finish and design
- Specify the right stainless steel

How Does A Stainless Steel Work?

Stainless steel is iron plus at least 11% chromium. If enough chromium is added, a protective passive film will form.



< 11% Chromium



> 11% Chromium

Major Alloying Elements

- Iron (Fe)
- Chromium (Cr)
 - Improves corrosion resistance
- Molybdenum (Mo)
 - Improves resistance to pitting and crevice corrosion caused by salt (chlorides) and pollution
- Nickel (Ni)
 - Improves ductility, toughness, and weldability
- Nitrogen (N)
 - Improves strength and pitting and crevice corrosion resistance

Families of Stainless Steels

- Austenitic
 - 300-series numbers (304, 316)
 - Strengthened by cold work
 - Nonmagnetic
- Ferritic
 - 400-series (430, 447)
 - Magnetic
- Duplex
 - Austenitic/ferritic (2205)
 - More corrosion resistant
 - Higher strength
 - Magnetic

Low Carbon or “L” Grades


- “L” refers to low carbon levels
 - Examples: 304L and 316L
- Specify “low carbon” for welding
- When there is no price premium for low carbon stainless steel, make it your standard specification

Architectural Stainless Steels


(Nominal Chemical Composition, Wt. Pct.)

	Cr	Ni	Mo	N	C, max
430	17	---	---	0.03	0.12
304	18	9	---	0.06	0.08
316	17	11	2	0.06	0.08
2205	22	5	3	0.15	0.03

Index of Relative Pitting Corrosion Resistance



Strength Comparison



Annual Cost of Metallic Corrosion

(US\$ billions)

- Total US Cost
 - Direct cost = \$296
 - Indirect cost = \$255.4
 - Total cost = \$551.4
- Construction*
 - Direct cost = \$50
 - Indirect cost = \$63.6
 - Total cost = \$113.6
 - Avoidable = 20 to 25%

* May be underestimated.
Does not include infrastructure
and industrial construction



Photos courtesy of Allegheny Ludlum and TMR Consulting

Two Piers, Progreso, Mexico

- Functioning pier
 - Built about 60 years ago (1937-1941)
 - Stainless rebar
- Non-functioning pier
 - Built about 30 years ago
 - Carbon steel rebar



Photo courtesy of the Nickel Institute

20-Year South African Exposure Data

Average Annual Corrosion Rate (mm/yr)

Metal	Severe Marine**	Severe Marine*	Marine**	Rural*
Type 316	0.0003	0.0001	0.00003	0.00003
Type 304	0.0004	0.0001	0.00008	0.00003
Type 430	0.002	0.0006	0.0004	0.00003
Al 3003	0.019	0.005	0.005	0.00028
Copper	0.025	0.04	0.009	0.00559
Zinc	0.111	NA	0.023	0.0033
Cor-Ten	0.810	1.15	0.212	0.0229
Mild Steel	2.190	0.846	0.371	0.0432

* Low pollution, ** Moderate pollution
National Building Research Institute, South Africa

Kure Beach, 57 Years

250 m (800 ft) from the ocean never washed



Type 304



Type 316

Photos courtesy of TMR Consulting

Kure Beach, 48 years

Carbon steel with 60 Zn, 20 Al, 20 Mg coating 250 m (800 ft) from the ocean




Photo courtesy of the Nickel Institute

Kure Beach, 58 years

Anodized aluminum, 250 m (800 ft) from the ocean



Photo courtesy of the Nickel Institute

Select Type 304

- Rural/suburban
- Urban areas
 - Low and moderate corrosivity
- Not suitable for salt exposure or moderate to high industrial pollution unless:
 - Smooth finish
 - Regular cleaning
 - Some staining between cleanings is acceptable



Gateway Arch, St. Louis, USA

Photo courtesy of the US National Parks Service

Select Type 316

- Urban areas
 - Moderate and high corrosivity
- Industrial
 - Low and moderate corrosivity
- Marine and deicing salt
 - Low to moderate corrosivity



Photos courtesy of the Nickel Institute

Frederick R. Weissman
Art Museum

Select More Corrosion Resistant Stainless Steels

- Industrial pollution
 - Developing countries
 - High sulfur dioxides levels
 - High particulate levels



Type 316 railings
Hong Kong Convention Center -
seawater spray exposure, rough finish

Photo courtesy of the Nickel Institute

Site and Design Evaluation System

- Designed for applications where corrosion staining is not acceptable
- Do not use this system if
 - Appearance does not matter
 - Structural integrity is the primary concern

Environmental Pollution


Points	Section 1: Environment (Select the highest applicable score)
	Rural
0	Very low or no pollution
	Urban Pollution (Light industry, automotive exhaust)
0	Low
2	Moderate
3	High *
	Industrial Pollution (Aggressive gases, iron oxides, chemicals, etc.)
3	Low or moderate
4	High *

* Potentially a highly corrosive location. Have a stainless steel corrosion expert evaluate the site.

Rating Pollution Levels

City	Pollution Level	Suspended Particulate $\mu\text{gm}/\text{m}^3$	Sulfur Dioxide $\mu\text{gm}/\text{m}^3$
Beijing	High	377	90
Calcutta	High	375	49
Stockholm	Low	9	5
Pittsburgh	Moderate	40	16
Moscow	High	100	109
New York	Moderate	27	26
Rio de Janeiro	High	139	129
Chicago	Moderate	35	14


Hydrogen ion concentration as pH from measurements made at the field laboratories, 2002



National Atmospheric Deposition Program/National Trends Network

<http://nadp.sws.uiuc.edu>

European Acid Rain Map



b/maps/prod/level3/id_1177.htm

Evaluation Scores

Section	Chicago	Pittsburgh
Environment	2	2



Pittsburgh,
Type 304



Chicago,
Type 316

Evaluation Score

Section	Museum	Window
Environment	2	2



Photos courtesy of the Nickel Institute

Weissman Art Museum, Type 316



Window frame,
Type 304

Evaluation Scores

Section	Miami Beach	Jones Beach
Environment	2	2



Photo courtesy of TMR

Miami Beach
light pole, Type 304



Photo courtesy of AISI

Jones Beach
light poles, Type 316

Evaluation Scores

Section	Singapore
Environment	2

Photos courtesy of Ewing Cole, Photographer: Erhard Pfeiffer



Singapore Turf Club,
Type 316 roof

Evaluation Scores

Section	Cheung Kong	Railings
Environment	3	3



Photo courtesy of Outokumpu

Cheung Kong Center,
Type 316



Photo courtesy of Nickel Institute

Hong Kong
Convention Center
railings, Type 316

Evaluation Score

Section	Canary Islands
Environment	0



Canary Island light pole, Type 316



Canary Island railing, 2205 stainless steel

Photos courtesy of Outokumpu

Evaluation Score

Section	Mapfre Tower
Environment	2

Mapfre Office Tower,
Barcelona, Type 316



Photo courtesy of ACERINOX

Evaluation Score

Section	Bank Boston
Environment	4

Bank Boston, São Paulo,
Brazil, Type 316



Photo courtesy of Núcleo Inox

Evaluation Scores

Section	Post	Gate
Environment	0	0

Australian Coastal fence,
Type 316 gate and Type 304 post



Photo courtesy of the Australian Stainless Steel Development Association

Coastal or Deicing Salt Exposure

Section 2: Coastal Exposure (Select the highest applicable score)
If there is exposure to both coastal and deicing salt, obtain assistance from a stainless steel corrosion expert

Points	Coastal or Marine Salt Exposure
1	Low (> 1.6 to 16 km (1 to 10 miles) from salt water) **
3	Moderate (30 m to 1.6 km (100 ft to 1 mile) from salt water)
4	High (< 30 m (100 ft) from salt water)
5	Marine (Some salt spray or occasional splashing) *
8	Severe Marine (Continuous splashing) *
10	Severe Marine (Continuous immersion) *

* Potentially a highly corrosive location.

Have a stainless steel corrosion expert evaluate the site.

** A sample from the site should be tested to determine if chlorides are present. Some locations of this type are exposed to chlorides but others are not.

Section 2: Deicing Salt (Chloride) Exposure (Select the highest applicable score). If there is exposure to both coastal and deicing salt, obtain assistance from a stainless steel corrosion expert

Points	Deicing Salt Exposure (Distance from road or ground)
0	No salt was detected on a sample from the site and no change in exposure conditions is expected.
0	Traffic levels on nearby roads are too low to generate road mist or wind levels are too low to carry chlorides to the site, and no deicing salt is used on sidewalks.
1	Very low salt exposure (≥ 180 m (600 ft) or 12 floors from salt source) **
2	Low salt exposure (30 to 180 m (100 to 600 ft) or up to 12 floors from salt source) **
3	Moderate salt exposure (< 30 m (100 ft) or 3 floors from salt source) **
4	High salt exposure (Direct application or splash zone) *

* Potentially a highly corrosive location.

Have a stainless steel corrosion expert evaluate the site.

** A sample from the site should be tested to determine if chlorides are present. Some locations of this type are exposed to chlorides but others are not.

Local Weather Patterns


Points	Section 3: Local Weather Pattern (Select only one)
-1	Temperate or cold climates, regular heavy rain
-1	Hot or cold climates with typical humidity below 50%
0	Temperate or cold climate, occasional heavy rain
0	Tropical or subtropical, wet, regular or seasonal very heavy rain
1	Temperate climate, infrequent rain, humidity above 50%
1	Regular very light rain or frequent fog
2	Hot, humidity above 50%, very low or no rainfall ***

*** If there is also salt or pollution exposure, have a stainless steel corrosion expert evaluate the site.

Critical Temperature/Humidity Combinations for Salt (Chloride) Corrosion


Critical Temperature °C (°F)	Critical Humidity Level, %		
	Sodium Chloride	Calcium Chloride	Magnesium Chloride
25 (77)	76	30	50
10 (50)	76	41	50
0 (32)	---	45	50

United States Chloride Deposition Map




Marine Corrosion, Metals Handbook Ninth Edition, Vol.13 Corrosion, ASM International

Australian Chloride Deposition Map



Downloaded from the CSIRO website <http://www.cmit.csiro.au>

United States and Canadian Corrosion Map



The Catalyst, Issue No. 2, 1997, ARMCO Inc.

Corrosion Map for Mexico




- Extremely severe
- Severe
- Moderate
- Mild
- Negligible

Map downloaded from <http://www.corrosion-doctors.org>

Corrosion Map for Central America



-  Extremely severe
-  Severe
-  Moderate
-  Mild
-  Negligible

Corrosion Map for Cuba



- Extremely severe
- Severe
- Moderate
- Mild
- Negligible

Map downloaded from <http://www.corrosion-doctors.org>

Corrosion Map for Venezuela



- Extremely severe
- Severe
- Moderate
- Mild
- Negligible

Map downloaded from <http://www.corrosion-doctors.org>

Brazilian Corrosion Map



Map downloaded from <http://www.corrosion-doctors.org>

- Extremely severe
- Severe
- Moderate
- Mild
- Negligible

Corrosion Map for Argentina



- Extremely severe
- Severe
- Moderate
- Mild
- Negligible

Map downloaded from <http://www.corrosion-doctors.org>

Corrosion Map for Chile



Map downloaded from <http://www.corrosion-doctors.org>

-  Extremely severe
-  Severe
-  Moderate
-  Mild
-  Negligible

Corrosion Map for Columbia



- Extremely severe
- Severe
- Moderate
- Mild
- Negligible

Map downloaded from <http://www.corrosion-doctors.org>

Corrosion Map for China



Map downloaded from <http://www.corrosion-doctors.org>

- Extremely severe
- Severe
- Moderate
- Mild
- Negligible


Corrosion Map for Japan

- Extremely severe
- Severe
- Moderate
- Mild
- Negligible



Map downloaded from <http://www.corrosion-doctors.org>

Corrosion Map for India




Map downloaded from <http://www.corrosion-doctors.org>

corrosion-doctors.org


Corrosion Map for New Zealand

Map downloaded from <http://www.corrosion-doctors.org>



Corrosion Map for Portugal

Map downloaded from <http://www.corrosion-doctors.org>




Corrosion Map for Spain



- Extremely severe
- Severe
- Moderate
- Mild
- Negligible

Map downloaded from <http://www.corrosion-doctors.org>


Corrosion Map for Great Britain



Map downloaded from <http://www.corrosion-doctors.org>

-  Extremely severe
-  Severe
-  Moderate
-  Mild
-  Negligible

Corrosion Map for South Africa



-  Extremely severe
-  Severe
-  Moderate
-  Mild
-  Negligible

Type 304 Stainless Steel Arbor

- Deicing salt exposure
- Rough, sand blasted finish
- Sculpture park
- Minneapolis, USA



Truck on elevated highway




Photos courtesy of Nickel Institute

Coastal Applications



Type 316

Type 304



Photos courtesy of Austral Wright Metals

Singapore Turf Club

Architect: Ewing Cole



Type 316 roof
2D finish

Curved 400 meter
long building and
walkway canopies


Standing seam roof

Modular design kept
costs down

Photo courtesy of Ewing Cole

Evaluation Scores

Section	Chicago	Pittsburgh
Environment	2	2
Deicing salt	3 or 4	2
Weather	-1	-1



Pittsburgh,
Type 304



Chicago,
Type 316

Evaluation Scores

Section	Museum	Window
Environment	2	2
Deicing salt	3	3
Weather	-1	-1



Photos courtesy of the Nickel Institute

Weissman Art Museum, Type 316



Window frame,
Type 304

Evaluation Scores

Section	Miami Beach	Jones Beach
Environment	2	2
Coastal salt	3	3
Weather	1	-1



Photo courtesy of TMR

Miami Beach
light pole, Type 304



Photo courtesy of AISI

Jones Beach
light poles, Type 316

Evaluation Score

Section	Singapore
Environment	2
Coastal salt	3
Weather	-1

Singapore Turf Club,
Type 316 roof

Photos courtesy of Ewing Cole, Photographer: Erhard Pfeiffer



Evaluation Scores

Section	Cheung Kong	Railings
Environment	3	3
Coastal salt	3	5
Weather	0	0



Hong Kong
Convention Center
railings, Type 316



Cheung Kong Center,
Type 316

Photo courtesy of Nickel Institute

Photo courtesy of Outokumpu

Evaluation Score

Section	Canary Islands
Environment	0
Coastal salt	3 to 5
Weather	1



Canary Island
light pole,
Type 316



Canary Island railing,
2205 stainless steel

Photos courtesy of Outokumpu

Evaluation Score

Section	Mapfre Tower
Environment	2
Coastal salt	3
Weather	1

Mapfre Office Tower,
Barcelona, Type 316



Photo courtesy of ACERINOX

Evaluation Score

Section	Bank Boston
Environment	4
Coastal salt	0
Weather	1

Bank Boston, São Paulo,
Brazil, Type 316



Photo courtesy of Núcleo Inox

Evaluation Scores

Section	Post	Gate
Environment	0	0
Coastal salt	4	4
Weather	0	0

Australian Coastal fence,
Type 316 gate and Type 304 post




Photo courtesy of the Australian Stainless Steel Development Association

Design Considerations

Points	Section 4: Design Considerations (Select all that apply)
0	Boldly exposed for easy rain cleaning
0	Vertical surfaces with a vertical or no finish grain
-2	Surface finish is pickled, electropolished, or roughness $\leq R_a 0.3 \mu\text{m}$ (12 μin)
-1	Surface finish roughness $R_a 0.3 \mu\text{m}$ (12 μin) $< X \leq R_a 0.5 \mu\text{m}$ (20 μin)
1	Surface finish roughness $R_a 0.5 \mu\text{m}$ (20 μin) $< X \leq R_a 1 \mu\text{m}$ (40 μin)
2	Surface finish roughness $> R_a 1 \mu\text{m}$ (40 μin)
1	Sheltered location or unsealed crevices***
1	Horizontal surfaces
1	Horizontal finish grain orientation

*** If there is also salt or pollution exposure, have a stainless steel corrosion expert evaluate the site.



Type 316 railings beside a beach

Specifying the surface roughness is as important as selecting the right stainless steel.





Photo courtesy of Austral Wright

No. 4 Finish Aluminum Oxide



R_a 0.7 μm (28 μin)

No. 4 Finish Silicon Carbide



$> R_a$ 0.3 μm (12 μin)



Typical Sheet Surface Roughness Range

Finish	2D	2B	BA	No. 3	No. 4	Hair-line	No. 7	No. 8	Super No. 8
R_a μ in	5 - 39	2.4 - 20	0.5 - 4	10 - 43	7 - 25	5.5 - 8.0	2.4 - 8	0.8 - 4	0.4 - 0.8
R_a μ m	0.13 - 1.0	0.06 - 0.5	0.01 - 0.10	0.25 - 1.1	0.18 - 0.64	0.14 - 0.2	0.06 - 0.2	0.02 - 0.10	0.01 - 0.02

Tighten Specifications


- Flatness
 - Require stretcher or tension leveling
- Chemistry
 - Sulfur ≤ 0.005 for exterior and swimming pool applications
- Iron Contamination
 - Require iron free certification in compliance with ASTM A 380
- Exterior and Swimming Pool Finishes
 - Surface roughness $\leq R_a 12 \mu\text{m}$ (20 μin)

Chloride Accumulation In Sheltered Locations



Sheltered Components

Increased corrosion risk



Photos courtesy of JSSA and ASSDA

Sites for Crevice Corrosion

If the design will be exposed to salt (chlorides) and moisture, avoid crevices or seal them to prevent corrosion




Photo courtesy of Nickel Institute

Type 316 Light Fixture

- Highly polished light fixture
- Unsealed crevices accumulated salt and water causing corrosion
- Eliminate corrosion by cleaning the fixture and sealing the crevices




Photo courtesy of Nickel Institute

- Coatings are not necessary, require regular replacement, and can cause corrosion
- Using the right stainless steel is more cost effective



Photos courtesy of Nickel Institute

Galvanic Corrosion Requires...

- Dissimilar metals
- Electrical connection between metals (i.e., metal-to-metal contact)
- Moisture is present and connects the metals

Solution

- Prevent direct metal to metal contact
 - Inert washers
 - Paint

Galvanic Series

Metals and Alloys in Sea Water

Magnesium

Zinc

Aluminum Alloys

Mild Steel

Low Alloy Steel

Cast Iron

Muntz Metal

Yellow Brass

Red Brass

copper

Aluminum Bronze

Silver

Stainless Steel

Monel

Gold




Anodic
More Likely to
corrode



More Noble
Cathodic




- Stainless steel fasteners in carbon steel cover
- Good ratio = no impact on corrosion rate
- Galvanized fasteners in stainless steel
- Bad ratio = rapid corrosion



Evaluation Scores

Section	Chicago	Pittsburgh
Environment	2	2
Deicing salt	3 or 4	2
Weather	-1	-1
Design	-1 to -2	2



Pittsburgh,
Type 304



Chicago,
Type 316

Evaluation Scores

Section	Museum	Window
Environment	2	2
Deicing salt	3	3
Weather	-1	-1
Design	-1	0



Photos courtesy of the Nickel Institute

Frederick R. Weissman Art Museum,
Type 316



Window frame,
Type 304

Evaluation Scores

Section	Miami Beach	Jones Beach
Environment	2	2
Coastal salt	3	3
Weather	1	-1
Design	3	-1



Photo courtesy of TMR

Miami Beach
light pole, Type 304



Photo courtesy of AISI

Jones Beach
light poles, Type 316

Evaluation Score

Section	Singapore
Environment	2
Coastal salt	3
Weather	-1
Design	-1

Singapore Turf Club,
Type 316 roof

Photos courtesy of Ewing Cole, Photographer: Erhard Pfeiffer



Evaluation Scores

Section	Cheung Kong	Railings
Environment	3	3
Coastal salt	3	5
Weather	0	0
Design	-1 or -2	2



Photo courtesy of Outokumpu

Cheung Kong Center,
Type 316



Hong Kong
Convention Center
railings, Type 316

Photo courtesy of Nickel Institute

Evaluation Score

Section	Canary Islands
Environment	0
Coastal salt	3 to 5
Weather	1
Design	-1 or -2



Canary Island light pole, Type 316



Canary Island railing, 2205 stainless steel

Photos courtesy of Outokumpu

Evaluation Score

Section	Mapfre Tower
Environment	2
Coastal salt	3
Weather	1
Design	0

Mapfre Office Tower,
Barcelona, Type 316



Photo courtesy of ACERINOX

Evaluation Score

Section	Bank Boston
Environment	4
Coastal salt	0
Weather	1
Design	-1

Bank Boston, São Paulo,
Brazil, Type 316



Photo courtesy of Núcleo Inox

Evaluation Scores

Section	Post	Gate
Environment	0	0
Coastal salt	4	4
Weather	0	0
Design	2	-1

Australian Coastal fence,
Type 316 gate and Type 304 post




Photo courtesy of the Australian Stainless Steel Development Association

Maintenance Schedule

Points	Section 5: Maintenance Schedule (Select only one)
0	Not washed
-1	Washed at least annually
-2	Washed four or more times per year
-3	Washed at least monthly

Evaluation Scores

Section	Chicago	Pittsburgh
Environment	2	2
Deicing salt	3 or 4	2
Weather	-1	-1
Design	-1 to -2	2
Maintenance	-1	0
Total	3	5



Pittsburgh,
Type 304



Chicago,
Type 316

courtesy of TMR Consulting

Evaluation Scores

Section	Museum	Window
Environment	2	2
Deicing salt	3	3
Weather	-1	-1
Design	-1	0
Maintenance	0	0
Total	3	4



Photos courtesy of the Nickel Institute

Weissman Art Museum, Type 316



Window frame,
Type 304

Evaluation Scores

Section	Miami Beach	Jones Beach
Environment	2	2
Coastal salt	3	3
Weather	1	-1
Design	3	-1
Maintenance	0	0
Total	9	3

Jones Beach
light poles, Type 316



Miami Beach
light pole, Type 304



Photo courtesy of TMR

Photo courtesy of AISI

Evaluation Score

Section	Singapore
Environment	2
Coastal salt	3
Weather	-1
Design	-1
Maintenance	0
Total	3

Singapore Turf Club,
Type 316 roof

Photos courtesy of Ewing Cole, Photographer: Erhard Pfeiffer



Evaluation Scores

Section	Cheung Kong	Railings
Environment	3	3
Coastal salt	3	5
Weather	0	0
Design	-1 or -2	2
Maintenance	-2	-3
Total	2 or 3	7



Photo courtesy of Outokumpu

Cheung Kong Center,
Type 316



Hong Kong
Convention Center
railings, Type 316

Photo courtesy of Nickel Institute

Evaluation Score

Section	Canary Islands
Environment	0
Coastal salt	3 to 5
Weather	1
Design	-1 or -2
Maintenance	0
Total	3 to 5



Canary Island
light pole,
Type 316



Canary Island railing,
2205 stainless steel

Photos courtesy of Outokumpu

Evaluation Score

Section	Mapfre Tower
Environment	2
Coastal salt	3
Weather	1
Design	0
Maintenance	-3
Total	3

Mapfre Office Tower,
Barcelona, Type 316



Photo courtesy of ACERINOX

Evaluation Score

Section	Bank Boston
Environment	4
Coastal salt	0
Weather	1
Design	-1
Maintenance	-2
Total	2

Bank Boston, São Paulo,
Brazil, Type 316



Photo courtesy of Núcleo Inox

Evaluation Scores

Section	Post	Gate
Environment	0	0
Coastal salt	4	4
Weather	0	0
Design	2	-1
Maintenance	0	0
Total	6	3

Australian Coastal fence,
Type 316 gate and Type 304 post



Photo courtesy of the Australian Stainless Steel Development Association

How Can I Reduce the Score?

- Design for rain washing
- Select smooth surface finishes
- Use vertical finish grain orientation
- Eliminate sheltered areas and horizontal surfaces
- Eliminate or seal crevices
- Design to facilitate manual washing
- Use natural or artificial barriers to reduce deicing salt road mist exposure

Standard Cleaning

- Rain
- Hot water power wash
- Mild chloride-free detergent
- Degreaser
 - 5% ammonia and water (window cleaners)
 - Alcohol
 - Vinegar and water
 - Citrus cleaner
- 200 mesh or finer calcium carbonate abrasive (except on colored or mirror-like finishes)



150 East 42nd Street, New York City
Cleaned for the first time after 30 years of service

Reusing Stainless Steel

525 William Penn Place
Pittsburgh, Pennsylvania
Completed in 1952

- Stainless entrance/lobby
- Lobby renovation in 2002
- Most of the stainless steel was refinished and reused

Before



After



Photos courtesy of IKM and Nickel Institute

Remedial Cleaning

- Adhesives
 - Alcohol, citric cleaner or other solvent recommended by adhesive supplier
- Paint and marker pens
 - Solvents or chemical paint remover and soft brush
- Cement or mortar
 - Rinse off with water while still wet
 - If it has dried, use power washing and if necessary abrasives

Embedded Iron Corrosion

- Remove by
 - Mechanical cleaning
 - Chemical cleaning (“Passivation”)
- Confirm cleaning by test to
 - ASTM A 967, Chemical Passivation Treatments for Stainless Steel Parts



Photo courtesy of Nickel Institute

Muriatic Acid Corrosion

- Tile, stone, masonry or concrete are sometimes cleaned with Muriatic (hydrochloric) acid
- Muriatic acid is very corrosive to stainless steel!
- Avoid Muriatic acid containing cleaners
- Use citric acid or other non-corrosive cleaners



Removing Welding Heat Tint

- Mechanical methods
 - Grinding
 - Abrasive blasting
- Chemical methods
 - Pickle paste
 - Pickling



Photo courtesy of ASSDA

Conclusions

- Carefully evaluate each site and application
- If technical questions arise, contact
(insert appropriate organization name)
- In more corrosive environments, have a metallurgical engineer with architecture experience evaluate the site and applications