

**Exhibit 2
FABRICATION PROPERTIES OF STAINLESS STEEL**

Readily heat-treatable for hardening and for mechanical properties

Physical and mechanical properties satisfactory for spinning

Readily joinable by soldering and brazing

Readily joinable by resistance welding

Readily shaped by deep drawing (cold)

Readily joinable by fusion welding

Readily formable by bending

Adaptable for hot forging

Machinability

Group	Type No.	UNS No.										
Austenitic	201	S20100	X	X	X	X	X	X	X	X	X	-
	202	S20200	X	X	X	X	X	X	X	X	X	-
	301	S30100	X	X	X	X	X	X	X	X	X	-
	302	S30200	X	X	X	X	X	X	X	X	X	-
	303	S30300	XX	X	-	-	-	-	X	-	-	-
	304	S30400	X	X	X	X	X	X	X	X	X	-
	304L	S30403	X	X	X	X	X	X	X	X	X	-
	305	S30500	X	X	X	X	X	X	X	X	XX	-
	309S	S30908	X	X	X	X	X	X	X	X	X	-
	310S	S31008	X	X	X	X	X	X	X	X	X	-
	316	S31600	X	X	X	X	X	X	X	X	X	-
	316L	S31603	X	X	X	X	X	X	X	X	X	-
	317	S31700	X	X	X	X	X	X	X	X	X	-
	317LMN	S31726	X	X	X	X	X	X	X	X	X	-
321	S32100	X	X	X	X	X	X	X	X	X	-	
347	S34700	X	X	X	X	X	X	X	X	X	-	
Ferritic	405	S40500	X	X	X	X	X	X	X	X	X	-
	430	S43000	X	X	X	X	X	X	X	X	X	-
	439	S43035	X	X	X	X	X	X	X	X	X	-
	430F	S43020	XX	X	-	-	-	-	X	-	-	-
	442	S44200	X	X	X	-	-	-	X	-	-	-
	446	S44600	X	X	X	X	-	-	X	-	X	-
Martensitic	403	S40300	X	X	X	X	-	X	X	-	X	X
	410	S41000	X	X	X	X	X	X	X	X	X	X
	416	S41600	XX	X	-	-	-	-	X	-	X	X
	420	S42000	X	X	-	-	-	-	X	-	X	X
	420F	S42020	XX	X	-	-	-	-	X	-	X	X
	440A	S44002	X	X	-	-	-	-	X	-	X	X
	440C	S44004	X	X	-	-	-	-	X	-	X	X
	440F	S44020	XX	X	-	-	-	-	X	-	X	X

X = Suitable for application. XX = Better adapted for application.